



warringtonfire
global safety

**T E L E T E X
FACSIMILE MESSAGE**

Holmesfield Road, Warrington, WA1 2DS

To Reply: Tel : +44 (0) 1928-635110

Fax : +44 (0) 1928-646672

Email : dean.owen@warringtonfire.net

Company :
Attention :
Fax No : 02476 694531
From : D J Owen
Date : 28th September 2006



No of Pages (Total) : 3

Attention Recipients: The information contained in this facsimile is confidential and may be subject to legal privilege. It is intended solely for the use of the individual or organisation to whom it is addressed and others authorised to receive it. If you are not the intended recipient, any use, disclosure, copying, distribution or taking of any action based on the contents is prohibited and may be unlawful. If you have received this communication in error, or if any problems occur with transmission, please notify us immediately by telephone on the above number.

TESTS CONDUCTED TO BS EN ISO 9239-1 and 11928-2 WF No.s 157687 & 157688

We confirm that the tests in accordance with BS EN ISO 9239-1 and 11928-2 have been conducted on specimens of your nominally 3mm thick carpet product tested loose laid upon a 6mm thick fibre cement board under cover of your purchase order number 7346.

The specimens were supplied by yourselves on the 1st September 2006. Bodycote Warringtonfire was not involved in any sampling or selection procedure.

Results Obtained:-

BS EN 11928-2 **PASS**

BS EN ISO 9239-1

Specimen No.	1	2	3	Mean
Max flame distance (cm)	11.0	10.0	-	9.67
Critical Radiant Flux (kW/m^2)	11.3	10.0	≥ 11.0	≥ 10.8
Smoke ($\%mk$)	0.0	1.28	0.0	0.0

This fax is for your information only and should not be used as a substitute for the formal report, which will include the full details required by the Standard. The test cannot be claimed to be in accordance with the Standard until the test report is issued.

On receipt of the completed tabular description as provided below relating to the specimens tested, we shall be pleased to issue our formal report relating to this investigation.